K.D. Langley Fiber Services

P.O. Box 7, Tiverton, RI 02878 • Telephone (401) 624-6868

September 21, 2006

Mr. Robert Dunbabin, Sr. President
Cascade Yarns
1224 Andover Park E
Tukwilla, WA 98118

Report on the Quantitative Fiber Analysis of Yarn

Material Submitted

One ball of knitting yarn, color blue, purported to contain 55% extra fine merino wool, 33% microfiber, 12% cashmere. The sample was identified as Cash Vero yarn.

Laboratory Procedure

Fibers were sectioned with a fiber cutter and mounted on microscope slides. Over 1000 fibers were identified using light microscopy at a magnification of 250-400X and the diameters of the fibers were measured. The acrylic fibers were chemically separated from the wool/cashmere fibers. All testing was performed in accordance with test methods AATCC 20-2004: Qualitative and AATCC 20A-2004: Quantitative.

Results

The sample contains 55.5% Wool, 32.9% Acrylic, 11.6% Cashmere.

Sincerely yours,

Kenneth D. Langley